



Received:03/30/2016 Completed:03/31/2016 Letter: E JB P.O.#: 38136 Test Report #: 3-12496-0-

Client's Identification Lot No.: 5062-10151. Date of Mfg: 12/9/2015. Style: Casablanca Sapphire S24786J. Product End Use: Upholstery.

Tested For: Ted Torres **Key Test: IMO 2010 Uph Cig** 235
 Uniroyal Global Engineered Products Inc.
 1800 2nd Street, Suite 970 **Tel: 1-(941)-906-8580 Ext:**
 Sarasota, FL 34236 **Fax: 1-()- -**

Category: Uph.Furniture(cig) Specifier: IMO LE 2012; V 5/15 PC: 16H /dl SM/mg

TEST PERFORMED: IMO 2010 FTP Code - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture

IGNITION SOURCE: Smouldering cigarette (section 3.1)

TEST ITEM COMPOSITE:

Cover Fabric --

- Client's cover fabric: (see "Client's Identification" section above)
- Standard cover fabric, 100% inherently flame retardant polyester fabric, approx. 220 g/m²

Filling Material --

- Non flame retardant flexible polyether foam, 22 kg/m³ (1.4 lb/ft³)
- Flame retardant polyurethane foam, Code Red II 35, 45 kg/m³ (2.8 lb/ft³)
- Non flame retardant flexible polyether foam, 22 kg/m³ (1.4 lb/ft³), wrapped with Uniguard fire blocking material
- Client's filling material: _____

RESULTS:

	Progressive Smouldering Within 1 hr After Start of Test (yes/no) -----	Flaming Within 1 hr After Start of Test (yes/no) -----
Initial Test:	No	No
Retest:	No	No



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Received:03/30/2016	Completed:03/31/2016	Letter: E	JB	P.O.#: 38136	Test Report #: 3-12496-0-
---------------------	----------------------	-----------	----	--------------	---------------------------

Client's Identification	Lot No.: 5062-10151. Date of Mfg: 12/9/2015. Style: Casablanca Sapphire S24786J. Product End Use: Upholstery.
--------------------------------	---

Tested For: Ted Torres Uniroyal Global Engineered Products Inc. 1800 2nd Street, Suite 970 Sarasota, FL 34236	Key Test: IMO 2010 Uph Cig Tel: 1-(941)-906-8580 Fax: 1-()- -	235 Ext:
---	---	-----------------

REMARKS: None.

FAILURE CRITERIA:


Progressive smouldering or flaming within one hour after start of test.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes; Fails

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

 AUTHORIZED SIGNATURE
 GOVMARK
 /pm lgb



Robert I. Brown

MAR 3 1 2016



Received:03/30/2016 Completed:03/31/2016 Letter: E1 JB P.O.#: 38136 Test Report #: 3-12496-1-

Client's Identification Lot No.: 5062-10151. Date of Mfg: 12/9/2015. Style: Casablanca Sapphire S24786J. Product End Use: Upholstery.

Tested For: **Ted Torres** Key Test: IMO 2010 Uph Propane Flame 345
 Uniroyal Global Engineered Products Inc.
 1800 2nd Street, Suite 970 Tel: 1-(941)-906-8580 Ext:
 Sarasota, FL, 34236 Fax: 1-()- -

Category: Uph. Furniture (propane) LE 2012; V 5/15 PC: 16H /dl SM/mg
 Specifier: IMO

TEST PERFORMED: IMO 2010 FTP Code - International Code for Application of Fire Test Procedures - Resolution MSC.307(88): Annex I - Fire Test Procedures, Part 8 - Test For Upholstered Furniture

IGNITION SOURCE: 20 seconds propane flame (section 3.2)

TEST ITEM COMPOSITE

Cover Fabric --

- Client's cover fabric: (see "Client's Identification" section above)
- Standard cover fabric, 100% inherently flame retardant polyester fabric, approx. 220 g/m³

Filling Material --

- Non flame retardant flexible polyether foam, 22 kg/m³ (1.4 lb/ft³)
- Flame retardant polyurethane foam, Code Red II 35, 45 kg/m³ (2.8 lb/ft³)
- Non flame retardant flexible polyether foam, 22 kg/m³ (1.4 lb/ft³), wrapped with Uniguard fire blocking material
- Client's filling material: _____

RESULTS:	Flaming* (seconds)	Glowing* (seconds)	Smoking* (seconds)	Smoldering* (seconds)
Initial Test:	0	0	20	20
Retest:	0	0	17	17

* Values are reported after removal of burner tube ignition source.

REMARKS: None.



96-D Allen Boulevard
 Farmingdale, New York 11735-5626 USA
 Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
 e-mail: testing@govmark.com

Received:03/30/2016	Completed:03/31/2016	Letter: E1	JB	P.O.#: 38136	Test Report #:	3-12496-1-
---------------------	----------------------	------------	----	--------------	----------------	------------

Client's Identification	Lot No.: 5062-10151. Date of Mfg: 12/9/2015. Style: Casablanca Sapphire S24786J. Product End Use: Upholstery.
-------------------------	---

Tested For: Ted Torres Uniroyal Global Engineered Products Inc. 1800 2nd Street, Suite 970 Sarasota, FL 34236	Key Test: IMO 2010 Uph Propane Flame	345 Tel: 1-(941)-906-8580 Fax: 1-()- -	Ext:
---	---	--	-------------

FAILURE CRITERIA:


Flaming, glowing, smoking, or smouldering which exceeds 120 seconds.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes; Fails

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

 AUTHORIZED SIGNATURE
 GOVMARK
 /pm /96



MAR 3 1 2016

Robert I. Brown