



GOVMARK

96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: testing@govmark.com

Received:07/12/2018 Completed:07/23/2018 Letter: G5 JB P.O.#: 4500027812 Test Report #: 3-27316-0-05

Client's Identification Item: 4002-01181. SPS-0227. Date of Mfg.: 6/28/18. Product End Use: Upholstery.

Tested For: **Kristi Rygh** Uniroyal Engineered Products, LLC
501 South Water Street Stoughton, WI 53589
Key Test: FAA 12-sec.Vert FAR 25.853(a) (Textiles) 175
Tel: 1-(608)-873-6631 Ext:
Fax: 1-()- -

Test Category: 12sec Vertical/Textiles Specifier:FAA LE 2018; V 3/18 PC:24H DL/jd
NTR 04/16

TEST PERFORMED: Vertical Test (12 seconds flame application) as per FAR Part 25, Appendix F, Part I(b) (4)

RESULTS ARE REPORTED: Initially; After laundering; After dry cleaning

PRODUCT CATEGORY: Textiles

REFERENCE: For Certain Textile Products Used in Compartment Interiors Transport Category, Airplanes: FAR 25.853(a) and Appendix F Part I(a) (1) (ii) [previously FAR 25.853(b)]

RESULTS:	Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Burn Length (inches)
Machine:	1	0.7	0	1.7
	2	0.6	0	1.7
	3	2.7	0	2.7
	Avg:	1.3	0	2.0
Cross Machine:	4	0.7	0	2.7
	5	0.0	0	2.3
	6	0.7	0	3.1
	Avg:	0.5	0	2.7

Burn Length Defined: Burn length is the distance from the original edge to the farthest evidence of damage to the test specimen due to flame impingement, including areas of partial or complete consumption, charring, or embrittlement, but not including areas sooted, stained, warped, or discolored, nor areas where material has shrunk or melted away from the heat source.

CONCLUSION: Based on the above Results and the Acceptance Criteria on page 2, the item tested:

Complies; Does not comply

Received: 07/12/2018	Completed: 07/23/2018	Letter: G5	JB	P.O.#: 4500027812	Test Report #: 3-27316-0-05
----------------------	-----------------------	------------	----	-------------------	-----------------------------

Client's Identification Item: 4002-01181. SPS-0227. Date of Mfg.: 6/28/18. Product End Use: Upholstery.

Tested For: Kristi Rygh Uniroyal Engineered Products, LLC 501 South Water Street Stoughton, WI 53589	Key Test: FAA 12-sec. Vert FAR 25.853(a) (Textiles) Tel: 1-(608)-873-6631 Ext: Fax: 1-()- -	175
--	---	-----

REMARKS: None.

ACCEPTANCE CRITERIA:

- Afterflame - 15.0 seconds maximum average
- Drip Burn - 5.0 seconds maximum average
- Burn Length - 8.0" maximum average

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified above.

----- Phyllis Pettit
 AUTHORIZED SIGNATURE
 SGS GOVMARK
 / jab  **AUG 02 2018**

(Page 2 of 2)